

| ARTICOLO<br>ARTICLE                                                                                 | AMBIENTE                                                                                                               |
|-----------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------------------|
| Materia prima   Raw material                                                                        | Pelli grezze europee   European raw hides                                                                              |
| Produzione   Manufacturing                                                                          | Made in Italy                                                                                                          |
| Dimensioni   Dimensions                                                                             | c.a 4,80 - 5,40 sqm                                                                                                    |
| Spessore   Thickness                                                                                | 1,1 - 1,2 mm                                                                                                           |
| Peso Specifico   Mass per Unit Area                                                                 | 620 - 980 g/qm in accordance with DIN 53327                                                                            |
| Solidità del colore alla luce<br>Light Fastness                                                     | > = 5 Class Blue Scale in accordance with DIN EN ISO 105-B02                                                           |
| Resistenza strappo pantalone<br>Tear Strenght, Single Edge Tear                                     | > = 20 N in accordance with DIN EN ISO 3377-1                                                                          |
| Resistenza alla Flessione<br>Flexing Resistance                                                     | 50.000 flexing/bending trials without damage in accordance with DIN EN ISO 5402                                        |
| Solidità del colore allo strofinio<br>Rubbing Fastness                                              | DIN EN ISO 11640 Veslic<br>> = 4 - 5 dry: 500 cycles<br>> = 4 - 5 wet: 250 cycles<br>> = 4 - 5 sweat (ph 8): 80 cycles |
| PH-Value                                                                                            | Minimum 3,5 cm in accordance with DIN EN ISO 4045                                                                      |
| Adesione alla Rifinitura<br>Adhesion of Finish                                                      | Minimum 2 N/cm in accordance with DIN EN ISO 11644                                                                     |
| Flammability<br> | CAL TB-117 (2013, Sec.1)<br>BS 5852: 1979, source 0-1<br>BS EN 1021-1-2:2006                                           |