

ARTICOLO ARTICLE	FORTALEZA
Materia prima Raw material	Pelli grezze europee European raw hydes
Produzione Manufacturing	Made in Italy
Dimensioni Dimensions	c.a 4,80 - 5,40 sqm
Spessore Thickness	1,1 - 1,3 mm
Peso Specifico Mass per Unit Area	620 - 980 g/qm in accordance with DIN 53327
Solidità del colore alla luce Light Fastness	> = 4 Class Blue Scale in accordance with DIN EN ISO 105-B02
Reisitenza strappo pantalone Tear Strenght, Single Edge Tear	> = 20 N in accordance with DIN EN ISO 3377-1
Resistenza alla Flessione Flexing Resistance	30.000 flexing/bending trials without damage in accordance with DIN EN ISO 5402
Solidità del colore allo strofinio Rubbing Fastness	DIN EN ISO 11640 Veslic > = 4 - 5 dry: 50 cycles > = 4 - 5 wet: 20 cycles > = 4 - 5 sweat (ph 8): 20 cycles
PH-Value	Minimum 3,5 cm in accordance with DIN EN ISO 4045
Adesione alla Rifinitone Adhesion of Finish	Minimum 2 N/cm in accordance with DIN EN ISO 11644
Flammability 	CAL TB-117 (2013, Sec.1) BS 5852: 1979, source 0-1 BS EN 1021-1-2:2006